

Silicone Foam Rubber

Saint-Gobain NORSEAL® F-20 is a medium density closed-cell silicone foam rubber product designed to deliver environmentally stable, flame-retardant performance for gasketing, insulation and dampening applications. NORSEAL F-20 offers excellent compression set resistance and is often the product of choice in aircraft, aerospace, mass transit, military and electronic applications with extremely stringent smoke, flame and toxicity requirements. F-20 offers excellent resistance to environmental conditions, making it an excellent choice for both indoor and outdoor sealing and gasketing applications.

NORSEAL F-20 is specially designed to provide the following features:

- Meets key industry standards: FAR 25.853, Bombardier SMP 800-C, NFPA 130, UL V0
- Recognized to UL 50E gasket and seals for electrical enclosures
- Non-toxic, low smoke generation and low flame spread
- Smooth surface on both sides for excellent sealing against air, dust, light and moisture
- Excellent compression set resistance
- Excellent resistance to ultraviolet light, ozone and extreme temperature ranges
- Meets requirements of FDA extractables 21.CFR177.2600 for food contact
- Closed-cell foam meets AMS 3195
- Non-corrosive for use with metals and in hostile environments
- Available as a pressure-sensitive adhesive tape under the NORSEAL Silicone SNS 520AF product line

Available Sizes

Standard thickness: .063, .125, .188, .25, .375 and .50 in. (1.6, 3.2, 4.8, 6.4, 9.6 and 12.7 mm)

Master roll size: 36 in. (914 mm) width. Length varies with thickness.

Special thickness and roll sizes also available.



Applications

- Trains
- Medical equipment
- Aerospace
- Street lamps

NORSEAL® F-20 – Properties

(COHRLastic® F-20)

Performance tests are run using standard test procedures. The values presented are typical values and should not be used for specification purposes.

Property	Unit of Measure	Value	Test Method
Physical			
Colors	–	Gray, Black	–
Tensile Strength	psi (kPa)	30 (207)	ASTM D412
Elongation at Break	%	60	ASTM D412
Density	lb.ft ³ (kg/m ³)	20 (320)	ASTM D3574
Compression Deflection	psi (kPa)	10 (70)	ASTM D1056
Compression Set (50% for 22 hrs. at 212°F)	%	<5	ASTM D1056 “D”
Surface Description	–	Smooth both sides	–
Flammability			
Flame Resistance (UL)	–	Pass	UL 94 V-0
Flame Resistance (FAR)	–	Pass	FAR 25.853 (12s & 60s)
Flame Spread Index	L _i	< 15	ASTM E162
Smoke Density	D ₂	1.5 minutes < 20 4.0 minutes < 50	ASTM E662
Toxic Gas Emissions Rating	–	Pass	SMP-800C
Flame Propagation	–	Pass	ASTM C1166
Environmental			
Stain Resistance	–	Pass	ASTM D925 - 06e2, Method A
Ozone Effect Rating	–	No cracking	ASTM D1171-99 (2007), Method A
UV Resistance	Visual	No degradation	SAE J1960
Water Absorption	%	< 1	ASTM D471 / D1056
Temperature Range	°C (F°)	-51 to +204 (-60 to +400)	–
FDA Extractables	–	Pass	21 CFR 177.2600 (food contact)
Gasket and Seals for Electronic Enclosures	–	Pass	UL 50E
Electrical and Thermal			
Dielectric Strength	volts/mil (VPM)	80	ASTM D149
Dielectric Constant	–	3.5	ASTM 150
Dissipative Factor	–	0.03	ASTM 150
Dry Arc Resistance	Seconds	127	ASTM D495
Volume Resistivity	ohms-cm	3.39 x 10 ¹⁴	ASTM 257
Thermal Conductivity	W/m°K	0.074	ASTM C518
Thermal Insulation (R-value)	ft. ² • h • F°/Btu • in	1.94	ASTM C518
Low Temperature Embrittlement	°C (F°)	-100 (-148)	DMA

Important Instructions

Because Saint-Gobain cannot anticipate or control every potential application, we strongly recommend testing of this product under individual application conditions prior to commercial use.

Shelf Life

10 years after the date of sale for base material when stored in original packaging at temperatures up to 70°F (21°C) and 50% relative humidity.

NORSEAL® and COHRLastic® are registered trademarks of Saint-Gobain Performance Plastics.



Saint-Gobain Performance Plastics

14 McCaffrey St.
Hoosick Falls, NY 12090
1-800-962-2666
Tel: (518) 686-7301
Fax: (518) 686-4840

foams@saint-gobain.com
www.foams.saint-gobain.com

The data and details in this document were correct and up-to-date at the time of printing and are intended to provide information on our products and their possible applications. It is the user's responsibility to obtain the latest version of the product data sheet. This data sheet is not a specification and does not assure specific product characteristics or make reference to the suitability of the product for a specific application. Because Saint-Gobain cannot anticipate or control every application, we strongly recommend testing of this product under individual application conditions. The application, use and conversion of this product are the user's responsibility.

Limited Warranty: For a period of 6 months from the date of first sale, Saint-Gobain Performance Plastics warrants this product(s) to be free from defects in manufacturing. Our only obligation will be to provide replacement product for any portion proving defective, or at our option, to refund the purchase price thereof. User assumes all other risks, if any, including the risk of injury, loss or damage, whether direct or consequential, arising out of the use, misuse, or inability to use this product(s). SAINT-GOBAIN PERFORMANCE PLASTICS DISCLAIMS ANY AND ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.

NOTE: Saint-Gobain Performance Plastics Corporation does not assume any responsibility or liability for any advice furnished by it, or for the performance or results of any installation or use of the product(s) or of any final product into which the product(s) may be incorporated by the purchaser and/or user. The purchaser and/or user should perform its own tests to determine the suitability and fitness of the product(s) for the particular purpose desired in any given situation.